


CLAIMS

1. An imaging element comprising a support having thereon, in order, at least one imaging layer, at least one interlayer containing a lubricant which provides scratch-resistance and at least one outermost layer containing a different
5 lubricant which provides abrasion-resistance.

2. An element according to claim 1 wherein the lubricant which provides abrasion-resistance is a silicone-based lubricant.

10 3. An element according to either of the preceding claims wherein the lubricant which provides abrasion-resistance is a siloxane having the formula (I):-



(I)

15 wherein each R₁ is independently an unsubstituted or substituted alkyl group having from 1 to 8 carbon atoms or an unsubstituted or substituted alkoxy group having from 1 to 8 carbon atoms, R₂ R₃, R₄ and R₅ each represents an unsubstituted or substituted alkyl, cycloalkyl, alkoxyalkyl, arylalkyl, alkoxy
aryloxyalkyl, glycidyloxyalkyl group or aryl group, and n and m each represents a
20 positive integer of from 0 to 2,500, with the proviso that both m and n cannot be 0.


4. An element according to claim 3 wherein in formula (I), each R₁ is the same and is an unsubstituted alkyl group having from 1 to 3 carbon atoms or an alkoxy group having either 1 or 2 carbon atoms.

25

5. An element according to either of claims 3 and 4 wherein R₂, R₃, R₄ and R₅ each represents an unsubstituted alkyl group.

6. An element according to any one of claims 3 to 5 wherein m is 0 and n is an integer from 2-500.

7. An element according to any one of the preceding claims wherein the lubricant which provides abrasion-resistance has a viscosity of 350 centistokes and an average molecular weight of 13,700 and has the formula:-



wherein n is an average of 183.

10

8. An element according to any one of the preceding claims wherein the lubricant which provides abrasion-resistance is present in a concentration of from about 35 to about 65 mg/m².

15

9. An element according to any one of the preceding claims wherein the lubricant providing scratch-resistance is a higher fatty acid or a derivative thereof or a higher alcohol or a derivative thereof.

20

10. An element according to claim 9 wherein the lubricant is a metal salt of a higher fatty acid, a higher fatty acid ester, a higher fatty acid amide or a polyhydric alcohol ester of a higher fatty acid.

25

11. An element according to either of claims 9 and 10 wherein the lubricant is a derivative of a fatty acid selected from the class consisting of palmitic, stearic, oleic, linoleic, linolenic or tauric acids.

12. An element according to claim 11 wherein the lubricant comprises 'Spermalube'.

30

13. An element according to any one of the preceding claims wherein the lubricant which provides scratch-resistance is present in a concentration of from about 15 to about 30 mg/m².
- 5 14. An element according to any one of the preceding claims wherein the element is selected from the class consisting of photographic, electrostatographic, photothermographic, electrothermographic, dielectric recording and thermal-dye-transfer imaging elements.
- 10 15. An element according to claim 14 wherein the element is a black-and-white photographic element in which at least one of the imaging layers comprises a radiation-sensitive silver halide emulsion layer.
- 15 16. An element according to claim 15 wherein the silver halide emulsion comprises a silver chlorobromide emulsion.
17. An element according to any one of the preceding claims wherein the element includes a nucleator capable of providing high contrast development in a latent-image forming layer.
- 20 18. An element according to anyone of the preceding claims which includes a booster.
- 25 19. A method for processing an imaging element according to any one of the preceding claims, which comprises developing the element with an alkaline developing solution.